



## Excelflex® Microporous Insulation

### Excelflex® Insulation Systems

Excelflex® Insulation Systems are the flexible version of Thermo Dyne's microporous insulation product line. The superior thermal performance of Excelflex® insulation allows the maximum amount of thermal protection to be provided within minimum space and weight requirements. Excelflex® microporous insulation is a blend of ceramic powders and fibers combined to produce a high temperature material that provides excellent thermal stability, low thermal diffusivity and the lowest thermal conductivity.

Excelflex® is specially formulated to block all three forms of heat transfer. Conduction is minimized through the use of a ceramic powder which intrinsically has low thermal conductivity. In addition, the powder is formed to create a porous structure, minimizing the energy conducted through the solid material. Convection is minimized by using a powder with an extremely fine particle size which forms void spaces too small for convection currents to exist. Radiation increasingly becomes the dominant mode of heat transfer as application temperature increases. The infrared heat transmission through the insulation is reduced to the lowest levels possible with the addition of special opacifiers in the Excelflex® formulation.

### Materials of Construction

Excelflex® Insulation Systems are composed of a high temperature core material which is encapsulated between two layers of high temperature cloth. This assembly is then compressed into a uniform thickness and density and then sewn to form the finished composite. The stitching provides structure, strength, and consistent distribution of the core material, while allowing the insulation to be flexible enough to be wrapped around irregular shapes.

The Excelflex® core material is an 1800°F continuous use material. Excelflex® Insulation Systems are supplied with a standard 1400°F S-Glass textile cloth covering, which provides the thermal stability necessary for most applications. Other textiles are available upon request which provide protection from 500°F to 2300°F. Thread material selection is based upon the application's temperature requirements. Excelflex® is available in standard (16pcf) and lightweight (10pcf) densities and thicknesses from 1/8" to 1/2".

### Excelflex® Insulation Systems Advantages

With a microporous core and versatile composite options, Excelflex® offers several major advantages over other insulation materials in high performance applications.

#### Lowest Thermal Conductivity

Microporous ceramic powders and fibers work together to form a material with the lowest possible thermal conductivity, thermal diffusivity and heat storage. This enables Excelflex® to provide the maximum thermal protection utilizing the least amount of weight and space.

#### Lightweight and Saves Space

Low core densities result in mass savings for weight sensitive applications commonly encountered in the Aerospace industry. In applications where space is a problem, low thermal conductivity means less material thickness is required to achieve the desired insulation value—saving space.

#### High Temperature Capability

Excelflex® can be manufactured to meet high temperature requirements including intermittent exposure up to 2300°F.

#### Flexible

The quilted stitch pattern provides strength, yet allows the composite to remain flexible enough to insulate irregular shapes.

#### Easy Fabrication


Complex shapes can be easily made by cutting Excelflex® with a sharp knife, razor, die or laser. Edges can be sealed by sewing on an edge strip of similar textile used on the composite.

### Typical Characteristics

Core Density	10 lbs/ft <sup>3</sup> , 16 lbs/ft <sup>3</sup>
Thickness	10pcf: 1/4", 3/8", 1/2" 16pcf: 1/8", 3/16", 1/4", 3/8", 1/2"
Textile Covering	Standard: S-Glass (1400°F) Available: E-Glass (1200°F) Silica (1800°F) Quartz (2000°F) Alumina-Boria-Silica (2300°F)
Stitching	Standard: 1" Square; lock stitched Available: Parallel stitched
Pad Size	Standard: 36"x 36" Available: 36"x 48" square lock stitched 36"x 72" parallel stitched

Other thicknesses and densities are available upon request.

### Excelflex® Compression Data For 16 pcf



### Thermal Conductivity Data (Btu - in/hr - ft<sup>2</sup> - °F)\*

Density = 10 lbs/ft<sup>3</sup>

Mean Temp.	1/4"	3/8"	1/2"
400°F	0.16	0.15	0.14
600°F	0.18	0.16	0.15
800°F	0.20	0.18	0.17
1000°F	0.23	0.20	0.19
1200°F	0.26	0.25	0.22

Density = 16 lbs/ft<sup>3</sup>

Mean Temp.	1/8"	3/16"	1/4"	3/8"	1/2"
400°F	0.17	0.16	0.15	0.14	0.13
600°F	0.19	0.18	0.17	0.15	0.14
800°F	0.22	0.19	0.18	0.16	0.15
1000°F	0.23	0.20	0.19	0.17	0.16
1200°F	0.24	0.21	0.20	0.19	0.18

\*NOTE: All thermal conductivity values have been measured in accordance with ASTM Test Procedure C-177. When comparing similar data, it is advisable to check the validity of all thermal conductivity values and ensure the resulting heat flow calculations are based on the same condition factors. Variations in any of these factors will result in significant differences in the calculated data.

### Application Example

Hot Face = 1800°F  
Cold Face = 250°F  
Ambient = 80°F  
Air flow = 0 mph

### Insulation Required

4", 8pcf Ceramic Fiber Blanket  
1.5", 16pcf Excelflex® Insulation Systems

### Result

Excelflex® Space Savings 62%  
Excelflex® Weight Savings 33%

Technical and installation support for Excelflex® microporous insulation is provided by Thermo Dyne's application engineering team. For more information on Excelflex® microporous insulation, contact Thermo Dyne Corporation at 219.295.4124 or Fax 219.293.0047.



### Aerospace/Defense

Engine nacelles  
Struts and cowlings  
Fire walls  
Flight data recorders  
Bleed air ducts  
Heat shields  
Auxiliary power units



### Industrial

Power plant pipes, ducts  
Incinerators  
Molten metal ladle backup  
Glass tank forehearth



### Commercial

Lab furnaces  
Gas boilers  
Appliances  
Night storage heaters  
Vending machines  
Exhaust systems



Thermo Dyne Corporation  
1006 Middlebury St., Elkhart, IN 46516  
574.295.4124, Fax: 574.293.0047  
www.ThermoDyne1.com

Form E-1000, Effective 7/01, ©2001, Thermo Dyne Corporation, All Rights Reserved Printed in USA

The information, recommendations, and opinions set forth herein are offered solely for your consideration, inquiry and verification and are not, in part or total, to be construed as constituting a warranty or representation for which we assume legal responsibility. Nothing contained herein is to be interpreted as authorization to practice a patented invention without a license. The following is a registered trademark of Thermo Dyne Corporation: Excelflex.